

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L6	266	(heat adj exchanger) and (aluminum with coat\$3 with resin)	USPAT; JPO; DERWEN T	2003/03/14 14:38
2	BRS	L7	21	6 and thermosetting	USPAT; JPO; DERWEN T	2003/03/14 14:38
3	BRS	L8	27	6 and nylon	USPAT; JPO; DERWEN T	2003/03/14 14:41
4	BRS	L9	19	6 and (nylon with resin)	USPAT; JPO; DERWEN T	2003/03/14 14:42
5	BRS	L10	42	6 and (polyester with resin)	USPAT; JPO; DERWEN T	2003/03/14 14:47
6	BRS	L11	10	6 and thermoplastic and polyester and nylon	USPAT; JPO; DERWEN T	2003/03/14 15:43
7	BRS	L13	2	6 and (vinylidene adj fluoride)	USPAT; JPO; DERWEN T	2003/03/14 14:52
8	BRS	L14	3	6 and (vinylidene with fluoride)	USPAT; JPO; DERWEN T	2003/03/14 14:53
9	BRS	L15	859	(aluminum with coat\$3 resin) and hydrophilic and (vinylidene adj fluoride)	USPAT; JPO; DERWEN T	2003/03/14 14:56
10	BRS	L16	14	15 and (heat adj exchanger)	USPAT; JPO; DERWEN T	2003/03/14 14:54

	Type	L #	Hits	Search Text	DBs	Time Stamp
11	BRS	L17	29	(aluminum with coat\$3 with resin) and hydrophilic and (vinylidene adj fluoride)	USPAT; JPO; DERWEN T	2003/03/14 14:59
12	BRS	L24	12	6 and polyester and nylon	USPAT; JPO; DERWEN T	2003/03/14 15:51
13	BRS	L33	18073	(thermoplastic with thermosetting) with resin	USPAT; JPO; DERWEN T	2003/03/14 16:01
14	BRS	L34	5895	33 and aluminum	USPAT; JPO; DERWEN T	2003/03/14 16:01
15	BRS	L35	72	34 and (heat adj exchanger)	USPAT; JPO; DERWEN T	2003/03/14 16:24
16	BRS	L36	12914	(thermoplastic or thermosetting) with (nylon or (vinylidene adj flouride))	USPAT; JPO; DERWEN T	2003/03/14 16:25
17	BRS	L37	6	((thermoplastic or thermosetting) with (vinylidene adj flouride))	USPAT; JPO; DERWEN T	2003/03/14 16:29
18	BRS	L38	0	((((thermoplastic or thermosetting) with (vinylidene adj flouride)) with resin)	USPAT; JPO; DERWEN T	2003/03/14 16:27
19	BRS	L39	5742	((thermoplastic or thermosetting) with nylon with resin)	USPAT; JPO; DERWEN T	2003/03/14 16:30
20	BRS	L40	1886	39 and aluminum	USPAT; JPO; DERWEN T	2003/03/14 16:30